



## ALT - 652 Gator-Aid®

### Mastic Alligatoring Patch (Exterior Use Only)

USER friendly, complies with all V.O.C. emissions and E.P.A. standards.

**GENERAL:** Gator-Aid® is a blend of an asphaltic emulsion, mineral fillers, fibers, ground rubber and plasticizers designed especially for alligatoring and raveled areas. It is also used for filling cracks in excess of 1" in width on any asphaltic surface. Economically, Gator-Aid® has superior advantages over hot mix skin patch asphalt that requires digging out the alligatoring areas and replacing them. It is ready to use on asphaltic surfaces such as athletic courts, driveways, roadways, highways, streets, parking lots, playgrounds, walkways, and running tracks.

**SURFACE**

**PREPARATION:** Surface must be dry and free from all loose material, dirt and dust.

**APPLICATION:** Mix well before using. Use as is. Pour on alligatoring areas and work in with flat blade squeegee. Gator-Aid® should be applied no thicker than ¼". Additional applications may be required in severe circumstances.

For Filling Cracks: Fill cracks. Before it sets up, scrape excess from surface (use V-shape rubber squeegee).

For Filling Bird Baths: Should be filled with lifts of ¼" in depth maximum and allowed to harden before any type of seal coating application.

Gator-Aid® will set under good conditions in several hours, depending on weather and filler thickness.

**COVERAGE:** Up to 20 ft.<sup>2</sup> for patching alligatoring areas and bird baths in ¼" depth. Up to 80 linear feet of ½" X ½" depth cracks.

**CAUTION:** **KEEP FROM FREEZING.** Do not use when rain is forecast, when surface is wet or when temperature is below 50°F. Wash tools in water. Use a paint thinner if material has dried. Do not store in direct sunlight or where temperatures exceed 100°F. Container should be closed when not in use. Keep out of the reach of children.

**PACKAGING:** 5 gallon pails and 55 gallon drums.

---

Material Specifications:

Requirements:

---

Weight per Gallon @ 77°F, ASTM D1010, (lbs) .....	10.40 – 10.80
Nonvolatile %, ASTM D2939 .....	67.00 - 70.00
Viscosity @ 77°F, ASTM D562 (Kreb's Stormer Unit) .....	125 min.
Penetration (0.1 mm), ASTM D5 .....	< 50
Resistance to water, ASTM D2939 .....	no blistering, no re-emulsification
Flammability .....	non flammable